Growth and stability of Pt on Au nanorods

He, D.S.; Han, Y.; Li, Z.Y.; Fennell, J.; Horswell, S.L.

DOI:

[10.1063/1.4751288](https://doi.org/10.1063/1.4751288)

License:

None: All rights reserved

Document Version

Publisher's PDF, also known as Version of record

Citation for published version (Harvard):

He, DS, Han, Y, Li, ZY, Fennell, J & Horswell, SL 2012, 'Growth and stability of Pt on Au nanorods', *Applied Physics Letters*, vol. 101, no. 11, 113102. <https://doi.org/10.1063/1.4751288>

[Link to publication on Research at Birmingham portal](#)

Publisher Rights Statement:

Eligibility for repository : checked 30/06/2014

General rights

Unless a licence is specified above, all rights (including copyright and moral rights) in this document are retained by the authors and/or the copyright holders. The express permission of the copyright holder must be obtained for any use of this material other than for purposes permitted by law.

- Users may freely distribute the URL that is used to identify this publication.
- Users may download and/or print one copy of the publication from the University of Birmingham research portal for the purpose of private study or non-commercial research.
- User may use extracts from the document in line with the concept of 'fair dealing' under the Copyright, Designs and Patents Act 1988 (?)
- Users may not further distribute the material nor use it for the purposes of commercial gain.

Where a licence is displayed above, please note the terms and conditions of the licence govern your use of this document.

When citing, please reference the published version.

Take down policy

While the University of Birmingham exercises care and attention in making items available there are rare occasions when an item has been uploaded in error or has been deemed to be commercially or otherwise sensitive.

If you believe that this is the case for this document, please contact UBIRA@lists.bham.ac.uk providing details and we will remove access to the work immediately and investigate.

Growth and stability of Pt on Au nanorods

D. S. He, Y. Han, J. Fennell, S. L. Horswell, and Z. Y. Li

Citation: [Applied Physics Letters](#) **101**, 113102 (2012); doi: 10.1063/1.4751288

View online: <http://dx.doi.org/10.1063/1.4751288>

View Table of Contents: <http://scitation.aip.org/content/aip/journal/apl/101/11?ver=pdfcov>

Published by the [AIP Publishing](#)

Articles you may be interested in

[Annealing effects of Au nanoparticles on the surface-plasmon enhanced p-Si/n-ZnO nanorods heterojunction photodetectors](#)

J. Appl. Phys. **115**, 173110 (2014); 10.1063/1.4875657

[Crystal growth behaviour in Au-ZnO nanocomposite under different annealing environments and photoswitchability](#)

J. Appl. Phys. **112**, 064308 (2012); 10.1063/1.4752469

[Noble metal nanodisks epitaxially formed on ZnO nanorods and their effect on photoluminescence](#)

Appl. Phys. Lett. **101**, 043122 (2012); 10.1063/1.4739516

[Nano scale phase separation in Au-Ge system on ultra clean Si\(100\) surfaces](#)

J. Appl. Phys. **111**, 104319 (2012); 10.1063/1.4721666

[Electrical, structural and microstructural characteristics of as-deposited and annealed Pt and Au contacts on chemical-vapor-cleaned GaN thin films](#)

J. Appl. Phys. **91**, 2133 (2002); 10.1063/1.1432127

This is a promotional banner for the 'Agilent Technologies Engineering Education & Research Resources DVD 2014'. The banner has a red top section with the text 'Agilent's Electronic Measurement Group is becoming Keysight Technologies.' Below this is a row of ten colorful icons representing various engineering fields: a green Wi-Fi symbol, a blue checkmark, a blue graduation cap, a green book, a yellow sun, a green molecular structure, a blue antenna, a purple microchip, a green wave, an orange traffic light, and a red starburst. To the left of these icons is a circular image of the DVD itself, which also features the Agilent logo and the year '2014'. Below the icons, the text 'Engineering Education & Research Resources DVD 2014' is written in a large, bold, black font. Underneath this, a smaller line of text says 'Agilent is the key to your test and measurement needs'. To the right of this text is a red button with the white text 'Order yours'. The bottom of the banner is a solid blue section with the Agilent Technologies logo (a stylized starburst) and the company name 'Agilent Technologies' in white.

Growth and stability of Pt on Au nanorods

D. S. He,¹ Y. Han,¹ J. Fennell,² S. L. Horswell,² and Z. Y. Li^{1,a)}

¹Nanoscale Physics Research Laboratory, School of Physics and Astronomy, University of Birmingham, Birmingham B15 2TT, United Kingdom

²School of Chemistry, University of Birmingham, Birmingham B15 2TT, United Kingdom

(Received 19 July 2012; accepted 23 August 2012; published online 10 September 2012)

We present a systematic study of Pt overgrowth on Au nanorods via a wet chemistry approach. The atomic resolved imaging provides direct evidence of initial epitaxial growth of Pt on the surface of Au nanorods, with a preferential deposition occurring at the rod ends. Over a period of one and half years, the carbon-supported nanorods are shown to have undergone a structural transformation when they are kept at ambient conditions, in contrast to the rods kept in solutions whose structure remains stable. Further controlled experiments show morphological changes of the nanorods upon annealing. We discuss the results in terms of the role that kinetics vs. thermodynamics plays in the observed phenomena. © 2012 American Institute of Physics. [<http://dx.doi.org/10.1063/1.4751288>]

Gold nanoparticles have been extensively investigated and can now be made in relatively large quantities with well-defined shapes and uniformities.^{1–3} They are often used as a platform for the deposition of an additional metal, which allows the chemical and physical properties of these bimetallic nanomaterials to be further modified by varying composition and chemical ordering.^{4–7} The Au-Pt bimetallic systems are particularly interesting for their potential applications as catalysts in the automobile industry, in which a long-term materials stability is essential.^{8,9}

It is well known that no solid solution can be formed between bulk Au and Pt.¹⁰ However, at a reduced length scale, the equilibrium structure of Au-Pt is still unclear.¹¹ Even though Luo *et al.* showed that AuPt alloyed particles (~2 nm) can be prepared using a two-phase synthesis protocol,¹² recent theoretical calculations suggest that a core-shell structure of Pt/Au with Au at the surface is preferred at the size of several hundred atoms.¹³ Further, there is overwhelming experimental evidence showing the chemical synthesis of Pt onto Au seed nanoparticles,^{14–19} though limited data are available at present in terms of the stability of these bimetallic nanoparticles with inversed chemical order.

In this study, we report our detailed characterization of Pt overcoated Au nanorods, via aberration-corrected scanning transmission electron microscopy (STEM) based techniques. We focus our attention on the growth mode and their long-term stability under controlled external environments.

Gold nanorods (Au NRs) were prepared using the seed mediated growth method reported by Nikoobakht and El-Sayed.²⁰ The synthesised gold nanorods were centrifuged at 6000 rpm for 20 min and re-dispersed in Milli-Q water twice to remove excess surfactant (cetyl trimethylammonium bromide—CTAB). Prior to Pt deposition, the Au NRs were centrifuged again at 6000 rpm for 20 min and re-dispersed in 0.1 M CTAB solution; the presence of CTAB enables reproducible Pt deposition on the Au NR surface to occur without further aggregation of particles. The Pt deposition was adapted from Grzelczak *et al.*¹⁸ Calculated amounts of the PtCl_4^{2-}

solution were mixed with 1 ml of the Au NRs for 30 min at 40 °C in order to achieve Pt:Au molar ratios of 0.05, 0.25, 0.5, and 0.75. This was followed by addition of a known amount of ascorbic acid (AA) to make a final AA:Pt ratio of 10:1 for all compositions. The solutions were kept at 40 °C for 20 h, during which time their color changed from purple to dark grey, indicative of the formation of Pt coverage on the Au NR surface. The resulting solution was centrifuged three times at 6000 rpm for 20 min and re-dispersed in Milli-Q water.

STEM observations were carried out using a JEOL 2100F microscope equipped with a CEOS aberration corrector, operated at acceleration energy of 200 kV. High angle annular dark field (HAADF) images were recorded using a JEOL ADF detector. The microscope is also equipped with a Bruker XFlash 4030 SDD detector, enabling energy dispersive x-ray spectroscopy (EDX) analysis.

Figure 1 shows STEM-HAADF images obtained from the as-grown Au nanorods (a) and Pt on Au nanorods with Pt:Au ratios of 0.05, 0.25, 0.50, and 0.75, in (b)–(e), respectively. A change in surface morphology with the increasing level of Pt coverage was apparent, where the initial growth preference was seen at the tips of the nanorods. Such a preferential growth persisted when the Pt:Au ratio was the highest, being 0.75 in our case, as evidenced by the corresponding nanorods becoming dumbbell-shaped, shown in Fig. 1(e).

The deposition of Pt onto Au nanorods was further confirmed by EDX mapping. Figures 2(a)–2(c) display elemental maps of Au, Pt, and Ag, respectively. Fig. 2(e) is the corresponding STEM-HAADF image taken from the same rod. The overlap of the elemental maps in Fig. 2(d) shows the relative location of Au and Pt, that support the overall core-shell structure, in agreement with the general picture accepted for the sequential chemical deposition of Pt on Au nanorods.¹⁹ The Ag signals are likely to arise from the residue from the synthesis of Au nanorods.

Atomically resolved STEM-HAADF imaging provides direct evidence that the initial Pt deposition follows an epitaxial growth mode on the surface of Au nanorods. Figure 3 is a representative image taken from the sidewall of AuPt nanorods, along the [100] zone axis. Pt and Au have similar atomic numbers ($Z = 78$ and 79 , respectively). Therefore, the

^{a)} Author to whom correspondence should be addressed. Electronic mail: Z.Li@bham.ac.uk.

FIG. 1. HAADF-STEM images taken from (a) the as-grown Au nanorods (NR), and Pt-coated Au NRs with Pt:Au ratios of (b) 0.05, (c) 0.25, (d) 0.50, and (e) 0.75. The 3D intensity profiles from an as-grown Au NR (arrowed) and a Pt-coated NR (arrowed) are inset in (a) and (b), respectively.

HAADF intensity difference can be attributed mainly to thickness contrast, rather than Z-contrast.^{21,22} This allows us to associate the sharp intensity variation appearing at the Au-Pt boundary to the island formation of Pt. Here, the Pt overlayer has a well-defined cube-on-cube orientation relationship with the underlying Au nanorods. This epitaxial

growth is seen in some areas to be extended up to 9 layers of Pt. Considering the difference in lattice parameters of bulk Au and Pt (see Table I), the observed epitaxial growth represents 3.9% lattice strain. The growth mechanism of Pt on crystalline Au(111) and (100) surfaces has been investigated yet remains controversial.⁵ It seems that the growth mode is strongly dependent on the conditions of the growth.

The overall AuPt core-shell structure observed in the present study is consistent with the sequence of the deposition. It would be interesting and important to investigate the stability of this structure from both a fundamental and a practical point of view. We found that the AuPt nanorods were stable over a prolonged period up to one and half years, if they were kept in the solution under ambient conditions. However, the morphology evolved over the same period if the nanorods on the standard TEM grids were stored in air

FIG. 2. EDX mapping of a AuPt nanorod with Pt:Au ratio of 0.75: (a) Au signal, (b) Pt signal, (c) Ag signal, and (d) overlapping of Au and Pt signals. The STEM image of the same rod is shown in (e).

FIG. 3. Atomic resolution HAADF-STEM images showing a Pt particle located on a side surface of a Au nanorod.

TABLE I. Summary of key parameters of Au and Pt for comparison. Data are taken from Refs. 23 and 24.

	Au	Pt
FCC, lattice parameter (Å)	4.08	3.92
Atomic radius (Å)	1.74	1.77
Cohesive energy (eV/atom)	3.81	5.48
Surface energy (J/m ²)	1.50	2.49

FIG. 4. HAADF-STEM images of AuPt nanorods with Pt:Au ratio of 0.25, after the nanorods were kept on TEM grids in ambient conditions for one and half years.

and at room temperature. This is evident from the image shown in Fig. 4, taken from an aged AuPt sample with a Pt:Au ratio of 0.25 composition. The image should be compared with the one shown in Fig. 1(c), which was taken from the same sample but immediately after its preparation from the solution. It seems that the original Au rod seeds had been dissolved or diffused.

The EDX elemental maps (Fig. 5(a)) of Au and Pt from the aged nanorods confirm that a void within the rod had been formed. It is possible that the original Pt islands may act as the nucleation sites for Au atoms. If this is the case, then the aged nanorods may represent an energetically stable equilibrium state for AuPt bimetallic nanoparticles. It is possible that the presence of surfactant and/or bromide in the solution stabilizes the original Au core-Pt shell structure and that this surfactant is wholly or partially removed under ambient condition.

To further study the driving force of the structural transformation, the AuPt nanorods on a TEM grid were annealed to 200 °C in vacuum of 10^{-6} mbar for 3 h. Similar morphology changes were again observed, though to a slightly lesser extent (see Fig. 5(b)). The result suggests that the initial sequentially deposited Au core Pt shell structure may be due to kinetic trapping. This hypothesis is supported by energetic considerations (Table I): the relatively low cohesive energy and low surface energy of Au in relation to Pt would favor the Au atoms on the surface. We speculate that the diffuse channels for Au atoms onto the Pt islands may be through the initial incomplete Pt coverage on Au seed rods. Blocking these gaps would increase the kinetic barriers for the diffusion of Au, potentially increasing the stability of the bimetallic rods.

FIG. 5. HAADF-STEM and corresponding EDX images of AuPt nanorods with Pt:Au ratio of 0.25, showing evolution of morphology: after the nanorods were kept on TEM grids in ambient condition for one and half year (a1-3); after the sample was annealed at 200 °C in vacuum for 3 h (b1-3).

In summary, we have shown that Pt deposited on Au nanorods via a wet-chemical route forms an overall core-shell structure, with direct evidence of initial Pt epitaxial growth on Au surfaces, followed by the formation of Pt islands on the Au nanorods. This structure undergoes significant changes when the supported rods are exposed to air or annealed at elevated temperatures, with signs that Au diffuses outwards to form either Pt-Au alloyed or Pt(core)Au(shell) nanoparticles. These findings provide insights of kinetic vs. thermodynamic roles played in structural morphology of Pt on Au seeded nanorods. They may also have implications in potential catalytic applications if Au nanoparticles are to be used as a seed platform for Pt.

We acknowledge the financial support from the UK EPSRC (Grant No. EP/G070326/1), the European Union through the FP7 Initial Training Network “ELCAT” (Grant No. 214936-2), and the COST Action MP0903. D.S.H. thanks the University of Birmingham and Chinese Scholarship Council for studentship. J.F. acknowledges financial support from the School of Chemistry, University of Birmingham, and the EPSRC (DTA Award Reference EP/P504678/1). The STEM instrument employed in this research was obtained through the Birmingham Science City project supported by AWM and ERDF.

¹Y. Xia, Y. J. Xiong, B. Lim, and S. E. Skrabalak, *Angew. Chem., Int. Ed.* **48**, 60 (2009).

²J. Perez-Juste, I. Pastorize-Santos, L. M. Liz-Marzan, and P. Mulvaney, *Coord. Chem. Rev.* **249**, 1870 (2005).

³K. Sohn, F. Kim, K. C. Pardo, J. S. Wu, Y. Peng, F. M. Zhou, and J. X. Huang, *ACS Nano* **3**, 2191 (2009).

⁴R. Ferrando, J. Jellinek, and R. L. Johnston, *Chem. Rev.* **108**, 845 (2008).

⁵L. L. Feng, X. C. Wu, L. R. Ren, Y. J. Xiang, W. W. He, K. Zhang, W. Y. Zhou, and S. S. Xie, *Chem.-Eur. J.* **14**, 9764 (2008).

⁶R. L. Chantry, W. Siriwatchcharapiboon, S. L. Horswell, A. J. Logsdail, R. L. Johnston, and Z. Y. Li, *J. Phys. Chem. C* **116**, 10312 (2012).

⁷Z. Y. Li, J. P. Wilcoxon, F. Yin, Y. Chen, R. E. Palmer, and R. L. Johnston, *Faraday Discuss.* **138**, 363 (2008).

⁸S. J. Guo, L. Wang, W. Wang, Y. X. Fang, and E. K. Wang, *J. Colloid Interface Sci.* **315**, 363 (2007).

⁹J. Gong, *Chem. Rev.* **112**, 2987 (2012).

¹⁰V. Ponec and G. C. Bond, *Catalysis by Metals and Alloys. Studies in Surface Science and Catalysis* (Elsevier, Amsterdam, 1995), Vol. 95.

¹¹J. A. Ascencio, C. Gutierrez-Wing, M. E. Espinosa, M. Marin, S. Tehuacanero, C. Zorrilla, and M. Jose-Yacaman, *Surf. Sci.* **396**, 349 (1998).

¹²J. Luo, M. M. Maye, V. Petkov, N. N. Kariuki, L. Wang, P. Njoki, D. Mott, Y. Lin, and C. J. Zhong, *Chem. Mater.* **17**, 3086 (2005).

¹³H. Liu, U. Pal, and J. Ascencio, *J. Phys. Chem. C* **112**, 19173 (2008).

¹⁴L. Yang, J. Chen, X. Zhong, K. Cui, Y. Xu, and Y. Kuang, *Colloids Surf., A* **295**, 21 (2007).

¹⁵J. Zeng, J. Yang, J. Y. Lee, and W. Zhou, *J. Phys. Chem. B* **110**, 24606 (2006).

¹⁶L. Lu, G. Sun, H. Zhang, H. Wang, S. Xi, J. Hu, Z. Tian, and R. Chen, *J. Mater. Chem.* **14**, 1005 (2004).

¹⁷S. Wang, N. Kristian, S. Jiang, and X. Wang, *Electrochem. Commun.* **10**, 961 (2008).

¹⁸M. Grzelczak, J. Perez-Juste, F. J. G. de Abajo, and L. M. Liz-Marzan, *J. Phys. Chem. C* **111**, 6183 (2007).

¹⁹M. Grzelczak, J. Perez-Juste, B. Rodriguez-Gonzalez, and L. M. Liz-Marzan, *J. Mater. Chem.* **16**, 3946 (2006).

²⁰B. Nikoobakht and M. A. El-Sayed, *Chem. Mater.* **15**, 1957 (2003).

²¹Z. Y. Li, in *Frontiers of Nanoscience: Metal Nanoparticles and Nanoalloys*, edited by R. L. Johnston and J. P. Wilcoxon (Elsevier, Oxford, 2012), Vol. 3.

²²Z. Y. Li, J. Yuan, Y. Chen, R. E. Palmer, and J. P. Wilcoxon, *Appl. Phys. Lett.* **87**, 243103 (2005).

²³C. Kittel, *Introduction to Solid State Physics*, 7th Ed. (John Wiley & Sons, New York, 1996).

²⁴S. Foiles, M. Baskes, and M. Daw, *Phys. Rev. B* **33**, 7983 (1986).