Hydrogen release and uptake in the Li–Zn–N system

Nguyen, Trang T.t.; Reed, Daniel; Book, David; Anderson, Paul

DOI:

[10.1016/j.jallcom.2014.12.190](https://doi.org/10.1016/j.jallcom.2014.12.190)

License:

Other (please specify with Rights Statement)

Document Version

Peer reviewed version

Citation for published version (Harvard):

Nguyen, TTT, Reed, D, Book, D & Anderson, P 2014, 'Hydrogen release and uptake in the Li–Zn–N system', *Journal of Alloys and Compounds*. <https://doi.org/10.1016/j.jallcom.2014.12.190>

[Link to publication on Research at Birmingham portal](#)

Publisher Rights Statement:

NOTICE: this is the author's version of a work that was accepted for publication. Changes resulting from the publishing process, such as peer review, editing, corrections, structural formatting, and other quality control mechanisms may not be reflected in this document. Changes may have been made to this work since it was submitted for publication. A definitive version was subsequently published as T.T.T. Nguyen, D. Reed, D. Book, P.A. Anderson, Hydrogen release and uptake in the Li–Zn–N system, *Journal of Alloys and Compounds* (2014), doi: <http://dx.doi.org/10.1016/j.jallcom.2014.12.190>

General rights

Unless a licence is specified above, all rights (including copyright and moral rights) in this document are retained by the authors and/or the copyright holders. The express permission of the copyright holder must be obtained for any use of this material other than for purposes permitted by law.

- Users may freely distribute the URL that is used to identify this publication.
- Users may download and/or print one copy of the publication from the University of Birmingham research portal for the purpose of private study or non-commercial research.
- User may use extracts from the document in line with the concept of 'fair dealing' under the Copyright, Designs and Patents Act 1988 (?)
- Users may not further distribute the material nor use it for the purposes of commercial gain.

Where a licence is displayed above, please note the terms and conditions of the licence govern your use of this document.

When citing, please reference the published version.

Take down policy

While the University of Birmingham exercises care and attention in making items available there are rare occasions when an item has been uploaded in error or has been deemed to be commercially or otherwise sensitive.

If you believe that this is the case for this document, please contact UBIRA@lists.bham.ac.uk providing details and we will remove access to the work immediately and investigate.

Accepted Manuscript

Hydrogen release and uptake in the Li–Zn–N system

Trang T.T. Nguyen, Daniel Reed, David Book, Paul A. Anderson

PII: S0925-8388(14)03118-1

DOI: <http://dx.doi.org/10.1016/j.jallcom.2014.12.190>

Reference: JALCOM 32979

To appear in: *Journal of Alloys and Compounds*

Please cite this article as: T.T.T. Nguyen, D. Reed, D. Book, P.A. Anderson, Hydrogen release and uptake in the Li–Zn–N system, *Journal of Alloys and Compounds* (2014), doi: <http://dx.doi.org/10.1016/j.jallcom.2014.12.190>

This is a PDF file of an unedited manuscript that has been accepted for publication. As a service to our customers we are providing this early version of the manuscript. The manuscript will undergo copyediting, typesetting, and review of the resulting proof before it is published in its final form. Please note that during the production process errors may be discovered which could affect the content, and all legal disclaimers that apply to the journal pertain.

Hydrogen release and uptake in the Li–Zn–N system

Trang T. T. Nguyen^a, Daniel Reed^b, David Book^b and Paul A. Anderson^{a*}

^a School of Chemistry, University of Birmingham, Edgbaston, Birmingham B15 2TT, UK

^b Department of Metallurgy and Materials, University of Birmingham, Edgbaston, Birmingham B15 2TT, UK

* Corresponding author: Tel: +44 (0) 121 414 4447; Email address: p.a.anderson@bham.ac.uk (Paul Anderson)

Abstract

Reactions of $\text{ZnCl}_2 + n\text{LiNH}_2$ at a range of molar ratios and temperatures gave a mixture of Zn_3N_2 and LiZnN as products; no stable amide chloride, imide chloride or nitride chloride phases were identified. Temperature-programmed desorption with mass spectrometry (TPD–MS) showed that the main gas emitted was ammonia (NH_3). The addition of lithium hydride (LiH) changed the main gaseous product from NH_3 to H_2 , which was released at a low temperature beginning around 90°C . Neither pure LiZnN nor Zn_3N_2 could be rehydrogenated under the conditions studied. However, mixtures of LiZnN and Zn_3N_2 , and LiZnN and LiCl reacted with H_2 at 300°C to form LiNH_2 and zinc metal.

Keywords:

lithium amide, zinc nitride, lithium zinc nitride, hydrogen absorption/desorption, reversible hydrogen storage, temperature-programmed desorption (TPD–MS)

1. Introduction

The Li–N–H system has attracted considerable attention as one of the most promising lightweight systems for reversible hydrogen storage. It involves cycling between LiNH_2 , Li_2NH and Li_3N [1–4]. However, the slow absorption kinetics and relatively high operating temperature currently limit its practical applications. To improve the system, a variety of ternary Li–M–N–H systems, where M = B, Ca, Al or Mg have also been investigated [5–8]. Amongst them, the Li–Mg–N–H system displays a remarkable improvement in the thermodynamics and kinetics of hydrogen desorption but the rate of reaction is still low below 200°C [9]. Some ternary systems incorporating transition metals *e.g.* the Li–Co–N–H system show a considerable improvement in desorption kinetics [10]. To investigate the effect of transition metals on the Li–N–H system, Ti, Fe, Ni or Cr were substituted for one of the Li sites in LiNH_2 , and Li–Ti–N–H showed a marked reduction in reaction enthalpy with $\Delta H_{\text{hyd}} = -46.6 \text{ kJmol}^{-1}$ compared with that of the Li–N–H system ($-75.67 \text{ kJmol}^{-1}$) [11].

Lithium and magnesium halides were also found to have significant effects on the hydrogen desorption properties of the Li–N–H system [12, 13]. Anderson *et al.* [12] heated LiNH_2 and Li_2NH with LiX and MgX_2 (X = Cl, Br, I) to form a range of new amide halides. On reaction with LiH , in all cases the halide-containing amides and imides released and absorbed hydrogen more rapidly than pure amides/imides.

In this study, we report the results of the reactions between ZnCl_2 and LiNH_2 , with and without the presence of LiH , under different conditions of stoichiometry and temperature. In contrast to the cases of LiCl and MgCl_2 [12], no stable amide chloride phases were isolated with reactions proceeding to the nitrides Zn_3N_2 and LiZnN at relatively low temperature. The hydrogen absorption/desorption properties of these products is investigated.

2. Experimental

2.1 Sample preparation

The LiNH_2 , ZnCl_2 , LiH (Sigma–Aldrich, > 95%) and Zn_3N_2 (Alfa–Aesar, 99%) starting materials were ground together in a pestle and mortar by hand in the desired mole ratio in an argon-atmosphere glovebox. The mixtures were then heated under flowing argon gas at temperatures from 150 to 600°C and held for up to 24 hours.

2.2 Temperature-programmed desorption with mass spectrometry (TPD–MS)

The sample ($\sim 0.1 \text{ g}$) was placed in a quartz reaction tube (7 mm O/D, 4 mm I/D) inside an argon-filled glovebox and sealed within the reaction chamber. The sealed reaction chamber was then transferred to a home-built temperature-programmed desorption apparatus detailed in previous work [5], connected to a quadrupole mass spectrometer (Hiden Analytical, HPR20), at a constant argon flow of 100 ml min^{-1} . In this study, all samples were heated at 2°C/minute to 400°C and held at that temperature for 2 hours before cooling.

2.3 Powder X-ray diffraction (XRD)

Powder X-ray diffraction data were collected on a Bruker D8 Advance diffractometer, operating in transmission geometry with monochromated $\text{Cu K}_{\alpha 1}$ radiation ($\lambda = 1.5406 \text{ \AA}$), and analysed using the Topas computer software [14].

2.4 Rehydrogenation

Samples were ground and sealed in a reaction vessel in an argon-atmosphere glovebox and then transferred to the

hydrogenation apparatus. Hydrogenation of the samples was attempted at 200 and 300°C under 90 bar H₂ for up to 24 hours.

3. Results and discussion

3.1 Zinc chloride and lithium amide

The reactions between ZnCl₂ and LiNH₂ were studied at molar ratios of 1:2, 1:3, 1:4, 1:5, and 1:6 in the temperature range 150–600°C. The heating rate was 2°C/minute and the reactions were kept at the set temperature for 12 hours.

For samples prepared at 150°C, along with ZnCl₂ and LiNH₂, LiCl was observed in the reaction products. The presence of LiCl is believed to result from a salt metathesis reaction such as that in Equation 1. Although Zn(NH₂)₂ was not observed in the XRD patterns, this may be present in finely divided or amorphous form, or may have reacted further to give another finely divided or amorphous product.

The reaction products from the samples prepared at 200°C contained a mixture of LiNH₂, Li₂NH, LiCl and ZnCl₂ (**Fig. S1**). A substantial proportion of LiNH₂ had decomposed into Li₂NH at 200°C. Previous research [15] reported that at this temperature LiNH₂ decomposed only to a limited extent. This improvement may be caused by the effect of the Cl[−] ion, which is in agreement with previous work. [12, 16].

At all reactant ratios the products after reaction at 250°C contained small amounts Zn₃N₂ and LiZnN. After heating to 300°C, no lithium amide or imide were observed at the ratio of 1:2, however, some remained at higher ratios of LiNH₂; no remaining ZnCl₂ was observed. The proportion of LiZnN present increased quickly when the temperature was raised to 400°C while that of Zn₃N₂ decreased. Except for the ratio of 1:2, at all other ratios the reactions seemed to be complete at 500°C, as the remaining Zn₃N₂ was converted into LiZnN (**Fig. 1**). At the ratio of 1:2, a considerable amount of Zn₃N₂ (38 wt %) remained at 500°C. It is believed that the 1:2 sample is deficient in Li (*vide infra*) preventing complete transformation of Zn₃N₂ into LiZnN. At 600°C, Zn₃N₂ was not observed. A small amount of LiZnN had been decomposed into LiZn and Zn as reported previously by Toyoura *et al.* [17].

These results suggest the reaction sequence given in Equations 2–4. ZnCl₂ and LiNH₂ may react in a 1:2 ratio to give Zn₃N₂ and LiCl with the release of ammonia (Equation 2). If further LiNH₂ is present a subsequent reaction with Zn₃N₂ is possible yielding LiZnN with the evolution of ammonia (Equation 3). These two reactions can be combined to give Equation 4.

Overall reaction:

The evolution of ammonia was confirmed by TPD–MS, where a broad peak at 280°C corresponding to ammonia gas was observed. A lesser amount of hydrogen gas was also observed beginning above 300°C and peaking at the higher temperature of about 400°C (**Fig. 2a**). The appearance of a small amount of hydrogen here may be from the decomposition of NH₃ [18]. It should be noted that although the 1:2 ratio should in principle yield Zn₃N₂ stoichiometrically according to Equation 2, both nitrides were observed under virtually all the reaction conditions and ratios studied, indicating that, once formed, Zn₃N₂ competes with ZnCl₂ to react with LiNH₂ *via* Equation 3.

3.2 Zinc chloride and lithium amide in the presence of lithium hydride

The reaction between ammonia and lithium hydride to yield lithium amide and hydrogen (Equation 5) has been demonstrated previously [18]

Lithium hydride was therefore added to the ZnCl₂–*n*LiNH₂ system in an attempt to change the overall reaction pathway to that given in Equation 6, which is the sum of Equations 4 and 5:

In practice, the addition of LiH resulted in not only the desired products of LiZnN and LiCl but also Zn (from 150°C) and LiZn (from 500°C). TPD–MS confirmed the main gaseous product changed from NH₃ to H₂ with an onset temperature of around 90°C (**Fig. 2b**). Hydrogen release at such a low temperature could be due to a metathesis reaction between ZnCl₂ and LiH to form LiCl and, transiently, ZnH₂, which is unstable above 90°C decomposing to form Zn and H₂ [19]. The decomposition of LiZnN to form LiZn and Zn was observed at the lower temperature of 500°C.

3.3 Zinc nitride and lithium amide

Zn_3N_2 (Alfa-Aesar, 99%) and LiNH_2 were mixed in a molar ratio of 1:3, in the temperature range 300–500°C for 1–24 hours, in order to produce pure LiZnN , *via* Equation 3, without the presence of LiCl . The reaction occurred slowly at 300°C with a small amount of LiZnN obtained and then faster at 400°C. At 500°C LiZnN (~92 wt.%) was achieved. A longer reaction time (24 hours) did not change the remaining Zn_3N_2 into LiZnN with a small amount of Zn_3N_2 (~6 wt.%) remaining.

In order to achieve pure LiZnN , excess LiNH_2 was added to the reactants, which were heated at 500°C for up to 12 hours. Pure LiZnN could be obtained after a 1 hour reaction between Zn_3N_2 and LiNH_2 , in a molar ratio of 1:4.2. The hydrogen desorption properties of the reaction between Zn_3N_2 and LiNH_2 were tested using TPD–MS. At about 360°C, ammonia release was observed, indicating the expected reaction (3) occurred (**Fig. 3a**).

3.4 Zinc nitride and lithium amide with the presence of lithium hydride

LiH was again added in order to change the overall reaction pathway in favour of hydrogen production (**Fig. 3b**). A ratio of 1:1:2 for Zn_3N_2 , LiNH_2 and LiH , was employed in accordance with the anticipated reaction given by Equation 7 (sum of Equations 3 and 5):

The products of reaction between Zn_3N_2 , LiNH_2 and LiH at 500°C for 2 hours were a mixture of LiZnN (~83 wt%) and Zn (~17 wt%). However, the reaction at 400°C for 2 hours achieved pure LiZnN .

Hydrogenation of a mixture of $\text{LiZnN} + 2\text{LiCl}$ (from the reaction of $\text{ZnCl}_2 + 3\text{LiNH}_2$ at 500°C) was attempted at 200–300°C for 12–24 hours under 90 bar H_2 . After 20 hours the mixture **Fig. 4a** showed the formation of LiNH_2 (21 wt%), along with Zn (32 wt%) and Li_2O (3 wt%). This indicates that rehydrogenation is possible, however, the presence and stability of LiCl may prevent the formation of ZnCl_2 , and therefore full reversibility may not be possible.

A mixture of LiZnN (~86 wt %) and Zn_3N_2 (~14 wt %), (from $\text{Zn}_3\text{N}_2 + 3\text{LiNH}_2$ at 500°C) was also rehydrogenated to form a mixture of Zn and LiNH_2 , in a molar ratio of approximately 1:1 (**Fig. 4b**). This is consistent with hydrogenation of LiZnN in accordance with the following reaction (Equation 8):

This result is potentially interesting as it shows that hydrogenation is not dependent on the presence of chloride and that higher gravimetric hydrogen contents may be obtained through investigation of the pure metal nitrides.

4. Conclusions

Reactions of $\text{ZnCl}_2 + n\text{LiNH}_2$ at a range of molar ratios and temperatures gave a mixture of Zn_3N_2 and LiZnN as products. No stable amide chloride, imide chloride or nitride chloride phases were identified. Temperature-programmed desorption with mass spectrometry (TPD–MS) showed that the main gas emitted during these reactions was ammonia (NH_3), but the addition of lithium hydride (LiH) changed the main gaseous product from NH_3 to H_2 , which was released at a low temperature beginning around 90°C. Hydrogenation of LiZnN was shown to occur in the presence of Zn_3N_2 or LiCl forming LiNH_2 and Zn metal.

Acknowledgments

We would like to thank Vietnam International Education Development, Ministry of Education and Training (VIED–MOET) for funding. Equipment used in this research was obtained through *Birmingham Science City (Hydrogen Energy and Advanced Materials 1 projects)* with support from Advantage West Midlands and partly funded by the European Regional Development Fund.

References

- [1] P. Chen, Z. Xiong, J. Lou, J. Lin, K.L. Tan, Interaction of hydrogen with metal nitrides and imides, *Nature* 420 (2002) 302–304.
- [2] P. Chen, Z. Xiong, J. Lou, J. Lin and K.L. Tan, Interaction between Lithium Amide and Lithium Hydride, *J. Phys. Chem. B* 107 (2003) 10967–10970.
- [3] T. Ichikawa, S. Isobe, N. Hanada, H. Fujii, Lithium nitride for reversible hydrogen storage, *J. Alloys Comp.* 365 (2004) 271–276.
- [4] S. Isobe, T. Ichikawa, N. Hanada, H.Y. Leng, M. Fichtner, O. Fuhr, H. Fujii, Effect of Ti catalyst with different chemical form on Li–N–H hydrogen storage properties, *J. Alloys Comp.* 404–406 (2005) 439–442.
- [5] P.A. Chater, P.A. Anderson, J.W. Prendergast, A. Walton, V.S.J. Mann, D. Book, W.I.F. David, S.R. Johnson, P.P. Edwards, *J. Alloys Comp.* 446–447 (2007) 350–354.
- [6] Z. T. Xiong, G. T. Wu, H. J. Hu, P. Chen, Ternary imides for hydrogen storage, *Adv. Mater.* 16 (2004) 1522–1525.
- [7] Y. Kojima, M. Matsumoto, Y. Kawai, T. Haga, N. Ohba, K. Miwa, S. Towata, Y. Nakamori, S. Orimo, Hydrogen absorption and desorption by the Li–Al–N–H system, *J. Phys. Chem. B* 110 (2006) 9632–9636.

- [8] Y. Nakamori, S. Orimo, Li–N based hydrogen storage materials, *Mat. Sci. Eng. B* 108 (2004) 48–50.
- [9] W. Lou, S. Sickafoose, Thermodynamic and structural characterization of the Mg–Li–N–H hydrogen storage system, *J. Alloys Comp.* 407 (2006) 274–281.
- [10] L. Ma, P. Wang, H. Dai, L. Kong, H. Cheng, Enhanced H-storage properties in Li–Co–N–H system by promoting ion migration, *J. Alloys Comp.* 466 (2008) L1–L4.
- [11] Q. Wang, Z. Chen, W. Yu, Y. Chen, Y. Li, Catalytic Effect of Transition Metal Doped in the Li–N–H System for Hydrogen Storage: A First Principle Investigation, *Ind. Eng. Chem. Res.* 49, (2010) 5993–5996.
- [12] P. A. Anderson, P. A. Chater, D. R. Hewett and P.R. Slater, Hydrogen storage and ionic mobility in amide–halide systems, *Faraday Discuss.* 151 (2011) 271–284.
- [13] H. Leng, Z. Wua, W. Duan, G. Xia, Z. Li, Effect of $MgCl_2$ additives on the H-desorption properties of Li–N–H system, *Int. J. Hydrogen Energy* 37 (2012) 903–907.
- [14] A.A. Coelho, Topas Academic v4.1, Brisbane 2007.
- [15] F.E. Pinkerton, Decomposition kinetics of lithium amide for hydrogen storage materials, *J. Alloys and Comp.* 400 (2005) 76–82.
- [16] J. Zhang, Y.H. Hu, Decomposition of lithium amide and lithium imide with and without anion promoter, *Ind. Eng. Chem. Res.*, 50 (2011) 8058–8064.
- [17] K. Toyoura, F. Oba, T. Ninomiya, A. Kuwabara, I. Tanaka, First-principles study of defect equilibria in lithium zinc nitride, *J. Phys. Condens. Matter.* 19 (2007), 046201.
- [18] Y. H. Hu and E. Ruckenstein, Ultrafast Reaction between LiH and NH_3 during H_2 Storage in Li_3N , *J. Phys. Chem. A* 107 (2003) 9737–9739.
- [19] E. Wiberg, W. Henle, Zur Kenntnis eines Zinkwasserstoffs ZnH_2 , *Z. Naturforsch.* 6b (1951) 393.

FIGURE CAPTIONS.

Fig. 1 Powder XRD patterns of the products of reactions between $ZnCl_2$ and $LiNH_2$ in a ratio of (a) 1:2, (b) 1:3, (c) 1:4, (d) 1:5, (e) 1:6, at 500°C for 12 hours.

Fig. 2 TPD–MS trace of the reaction of $ZnCl_2$ and $LiNH_2$ (a) without and (b) with LiH heated at 2°C min^{−1} to 400°C, showing traces for hydrogen (blue), ammonia (red) and temperature (green).

Fig. 3 TPD–MS trace of the reaction of Zn_3N_2 and $LiNH_2$ (a) without and (b) with LiH heated at 2°C min^{−1} to 400°C, showing traces for hydrogen (blue), ammonia (red) and temperature (green).

Fig. 4 (a) Powder XRD pattern of the products of the hydrogenation of a mixture of $LiZnN$ and $LiCl$ under 90 bar H_2 , at 300°C for 20 hours showing observed (blue), Rietveld fit (red) and difference (grey) plots. (b) Powder XRD pattern of a mixture of $LiZnN$ (86 wt%) and Zn_3N_2 (14 wt%) before (lower trace) and after (upper trace) hydrogenation at 300°C for 20 hours.

Fig. S1 Powder XRD patterns of the products of reactions between $ZnCl_2$ and $LiNH_2$ in a ratio of (a) 1:2, (b) 1:3, (c) 1:4, (d) 1:5, (e) 1:6, at 200°C for 12 hours.

Highlights

- Reactions of $\text{ZnCl}_2 + n\text{LiNH}_2$ gave a mixture of Zn_3N_2 and LiZnN as products.
- No stable amide chloride, imide chloride or nitride chloride phases were identified.
- The addition of lithium hydride (LiH) changed the main gaseous product from NH_3 to H_2 .
- Neither pure LiZnN nor Zn_3N_2 could be rehydrogenated under the conditions studied.
- $\text{LiZnN}/\text{Zn}_3\text{N}_2$, and LiZnN/LiCl mixtures hydrogenated at 300°C to form LiNH_2 and Zn metal.