

Biomimetic materials to characterize bacteria-host interactions

Stones, Daniel; Al-Saedi, Fitua; Vaz, Diana; Perez Soto, Nicolas; Krachler, Anne Marie

DOI:
[10.3791/53400](https://doi.org/10.3791/53400)

License:
None: All rights reserved

Document Version
Peer reviewed version

Citation for published version (Harvard):
Stones, D, Al-Saedi, F, Vaz, D, Perez Soto, N & Krachler, AM 2015, 'Biomimetic materials to characterize bacteria-host interactions', *Journal of Visualized Experiments*, no. 105, e53400. <https://doi.org/10.3791/53400>

[Link to publication on Research at Birmingham portal](#)

General rights

Unless a licence is specified above, all rights (including copyright and moral rights) in this document are retained by the authors and/or the copyright holders. The express permission of the copyright holder must be obtained for any use of this material other than for purposes permitted by law.

- Users may freely distribute the URL that is used to identify this publication.
- Users may download and/or print one copy of the publication from the University of Birmingham research portal for the purpose of private study or non-commercial research.
- User may use extracts from the document in line with the concept of 'fair dealing' under the Copyright, Designs and Patents Act 1988 (?)
- Users may not further distribute the material nor use it for the purposes of commercial gain.

Where a licence is displayed above, please note the terms and conditions of the licence govern your use of this document.

When citing, please reference the published version.

Take down policy

While the University of Birmingham exercises care and attention in making items available there are rare occasions when an item has been uploaded in error or has been deemed to be commercially or otherwise sensitive.

If you believe that this is the case for this document, please contact UBIRA@lists.bham.ac.uk providing details and we will remove access to the work immediately and investigate.

1 **Biomimetic materials to characterize bacteria-host interactions**

2

3 **AUTHORS:**

4 Stones, Daniel H*

5 Institute of Microbiology and Infection

6 School of Biosciences

7 University of Birmingham

8 Birmingham, UK

9 d.stones@bham.ac.uk

10

11 Al-Saedi, Fitua*

12 Institute of Microbiology and Infection

13 School of Biosciences

14 University of Birmingham

15 Birmingham, UK

16 fma332@bham.ac.uk

17

18 Vaz, Diana

19 Institute of Microbiology and Infection

20 School of Biosciences

21 University of Birmingham

22 Birmingham, UK

23 d.p.vaz@bham.ac.uk

24

25 Perez-Soto, Nicolas

26 Institute of Microbiology and Infection

27 School of Biosciences

28 University of Birmingham

29 Birmingham, UK

30 nap375@bham.ac.uk

31

32 *These authors have contributed equally.

33

34 **CORRESPONDING AUTHOR:**

35 Krachler, Anne M

36 Institute of Microbiology and Infection

37 School of Biosciences

38 University of Birmingham

39 Birmingham, UK

40 a.krachler@bham.ac.uk

41

42 **KEYWORDS:**

43 Host-pathogen interaction, bacterial adhesion, host cell attachment, adhesin, biomimicry,

44 bioengineering, chemical biology

45 **SHORT ABSTRACT:**

46

47 Bacterial attachment to host cells is a key step during host colonization and infection. This
48 protocol describes the generation of polymer-coupled recombinant adhesins as biomimetic
49 materials which allow analysis of the contribution of individual adhesins to these processes,
50 independent of other bacterial factors.

51

52 **LONG ABSTRACT:**

53

54 Bacterial attachment to host cells is one of the earliest events during bacterial colonization of
55 host tissues and thus a key step during infection. The biochemical and functional
56 characterization of adhesins mediating these initial bacteria-host interactions is often
57 compromised by the presence of other bacterial factors, such as cell wall components or
58 secreted molecules, which interfere with the analysis. This protocol describes the production
59 and use of biomimetic materials, consisting of pure recombinant adhesins chemically coupled
60 to commercially available, functionalized polystyrene beads, which have been used successfully
61 to dissect the biochemical and functional interactions between individual bacterial adhesins
62 and host cell receptors. Protocols for different coupling chemistries, allowing directional
63 immobilization of recombinant adhesins on polymer scaffolds, and for assessment of the
64 coupling efficiency of the resulting “bacteriomimetic” materials are also discussed. We further
65 describe how these materials can be used as a tool to inhibit pathogen mediated cytotoxicity
66 and discuss scope, limitations and further applications of this approach in studying bacterial -
67 host interactions.

68

69 **INTRODUCTION:**

70

71 Dissecting the interactions between bacterial adhesins and host surface receptors at the host-
72 pathogen interface is an essential step towards our understanding of the underlying
73 mechanisms driving bacterial adhesion. Ultimately, this will help us to identify strategies to
74 interfere with these processes during infections. In conducting such studies, we often face a
75 dilemma: Biochemical and biophysical analysis of the molecular mechanisms of adhesin binding
76 requires their separation from other cell wall components, which may interfere with adhesion
77 events. On the other hand, the use of recombinant soluble proteins over-simplifies the
78 adhesion event, by disregarding protein anchoring in the bacterial cell wall and multivalency of
79 binding achieved through bacterial surface display. Equally, from the host cell’s perspective,
80 encountering and binding to single adhesin molecules does not always have the same impact in
81 terms of plasma membrane organization, membrane fluidity and receptor clustering¹ and this,
82 ultimately, makes it difficult to evaluate the impact of adhesion on host cellular signaling and
83 the outcome of bacteria-host interactions.

84

85 Recently a method was devised, whereby recombinant purified adhesins or adhesin fragments
86 are directionally and covalently coupled to polymer particles similar in size to bacteria, thus
87 mimicking bacterial surface display. This approach has been used on a range of different
88 adhesins, from Gram-negative Multivalent Adhesion Molecules (MAMs)^{2, 3}, to Gram-positive

89 adhesins including *Staphylococcus aureus* fibronectin binding protein (FnBPA)^{4, 5} and
90 *Streptococcus pyogenes* F1^{6, 7}. This method has allowed the dissection of adhesin fragments
91 important for host cell binding, identification of host surface receptors and determination of
92 their behavior on the host cell surface, while taking both binding affinity and avidity into
93 consideration^{1, 8}. Additionally, this approach has been used to investigate the efficacy of
94 immobilized adhesins and derivatives as inhibitors of host-pathogen interactions^{8, 9}. It has been
95 demonstrated that surface coupled derivatives of the *Vibrio parahaemolyticus* Multivalent
96 Adhesion Molecule (MAM) 7 can be used to attenuate a range of bacterial infections *in vitro*,
97 including those caused by multidrug-resistant pathogens such as *Acinetobacter baumannii* and
98 methicillin-resistant *S. aureus* (MRSA)^{7, 9}.

99
100 Herein, we describe different chemistries which can be used to immobilize adhesins to
101 commercially available functionalized polystyrene particles. Due to the wide array of available
102 surface functionalities, labels and particle sizes, these are a useful scaffold for the production of
103 bacteriomimetic materials to investigate adhesin-host interactions. We further describe
104 methods for the initial characterization of the coupling reaction, and for the calculation of
105 important properties of the resulting materials. Finally, the use of bead-coupled adhesins as
106 competitive inhibitors of *in vitro* bacterial infections is discussed as an example of their
107 application, as well as the future scope and limitations of this approach.

108 **PROTOCOL:**

109 **1. Chemical coupling of proteins to polymer beads**

110 **1.1. Thiol-amine directional coupling**

111 Note: This protocol is suitable for coupling of cysteine containing proteins to amine-
112 functionalized polymer beads, using Sulfosuccinimidyl 4-(*p*-maleimidophenyl)butyrate (Sulfo-
113 SMPB) as cross-linking agent (Figure 1).

114
115 **[Place Figure 1 here]**

116 **1.1.1 Preparation of reagents:**

117 1.1.1.1 Prepare PBS (100 mM sodium phosphate, 150 mM NaCl, pH 7.0) and autoclave.

118 1.1.1.2 Prepare a 100x stock (0.5 M or 287 mg/ml in PBS) of TCEP (tris(2-
119 carboxyethyl)phosphine) immediately before use.

120 1.1.1.3 Prepare a 5x stock (10 mM or 4.58 mg/ml in dH₂O) of Sulfo-SMPB immediately prior to
121 use.

122 1.1.1.4 Prepare a 10x stock (500 mM or 88 mg/ml in PBS, pH 7.0) of cysteine immediately
123 before use.

133

134 **1.1.2 Bead activation:**

135

136 1.1.2.1 Mix the bead suspension by gently inverting and transfer the required amount of bead
137 suspension (e.g., 12 μ l) into a sterile 1.5 ml tube containing 1 ml sterile PBS, pH 7.0.

138 1.1.2.2 Gently pipette up and down to wash the beads and pellet by centrifugation in a
139 microcentrifuge (2 minutes at 16000 x g).

140 1.1.2.3 Carefully remove the supernatant with a pipette and discard.

141 1.1.2.4 Resuspend the bead pellet in 1 ml of fresh sterile PBS and repeat the washing step.

142 1.1.2.5 Resuspend the bead pellet in 0.8 ml of PBS.

143 1.1.2.6 Add 200 μ l of freshly prepared 10 mM Sulfo-SMPB, to give a final concentration of 2
144 mM.

145 1.1.2.7 Incubate the bead suspension for 1 hour at 25 °C on a rotating wheel.

146 **1.1.3 Protein reduction:**

147 1.1.3.1 During the incubation period of the activation step, prepare the protein for the
148 following coupling step so it can be immediately added to the activated beads.

149 Note: Although this reduction step is not always required for GST (Glutathione S-transferase)
150 fusion proteins, it is recommended to ensure a high coupling efficiency.

151 1.1.3.1.1 Check the protein concentration, and adjust it to the final concentration required
152 for the coupling reaction. Note: 6 μ M protein in PBS, and a volume of 1 ml are usually used.

153 1.1.3.1.2 Add TCEP stock to give a final concentration of 5 mM.

154 1.1.3.1.3 Incubate the solution for 30 minutes at room temperature.

155 Note: The reaction mixture can be directly used for the following coupling reaction.

156 1.1.3.1.4 Retain a small amount (a few μ l) of the protein solution for determining the
157 protein concentration and calculation of coupling efficiency (see section 2).

158 **1.1.4 Protein coupling step:**

159 1.1.4.1 Pellet the activated beads by centrifugation (2 minutes, 16000 x g in a microcentrifuge),
160 and wash the pellet once in 1 ml of fresh sterile PBS.

161 1.1.4.2 Resuspend the pellet in the prepared protein solution (e.g., 1 ml), to give the desired
162 protein concentration.

163 Note: The protein concentration during the coupling step will depend on the average coupling
164 efficiency (see section 2 for determination of the coupling efficiency) and desired coupling
165 density (as calculated in 1.1.4.3). The efficiency is approximately 85% and the desired final
166 concentration 5 μM in the 10x bead suspension, so protein concentration during the coupling
167 step should be approximately 6 μM .

168 1.1.4.3 Calculate the coupling density using the following formula:

169

$$\text{coupling density } \rho_c = \frac{\text{protein conc}}{\text{protein } M_w} \cdot \frac{6 \cdot 10^{23}}{\text{bead conc}} \cdot \frac{1}{\pi d^2}$$

170

171 where

172

173 ρ_c coupling density [number of protein molecules/ nm^2],

174 protein conc protein concentration [mg/ml],

175 protein M_w protein molecular weight [Da],

176 bead conc bead concentration [number of beads/L],

177 d bead diameter [nm^2]

178 $6 \cdot 10^{23}$ Avogadro's number

179

180 1.1.4.4 Use the coupling density to calculate the average ligand spacing:

181

$$\text{average ligand spacing [nm]} = \sqrt{\frac{1}{\rho_c}}$$

182 1.1.4.5 Incubate the protein-bead suspension for 2 hours at 25 $^\circ\text{C}$ on a rotating wheel.

183 Note: Some proteins may not be stable at room temperature. In these cases, the reaction can
184 be carried out at 4 $^\circ\text{C}$ overnight.

185 1.1.4.6 Deactivate remaining activated groups on the beads by adding cysteine stock to a final
186 concentration of 50 mM and incubate the suspension for 30 minutes at 25 $^\circ\text{C}$ on a rotating
187 wheel.

188 1.1.4.7 Pellet the beads by centrifugation (2 minutes, 16000 x g in a microcentrifuge).

189 1.1.4.8 Keep the supernatant for determining the protein concentration and calculation of
190 coupling efficiency (see section 2).

191 1.1.4.9 Wash the bead pellet twice with 1 ml PBS and resuspend in 1 ml fresh PBS to give the
192 final product.

193 Note: The above protocol will typically give 1 ml of coupled protein, at a final concentration of 5
194 μM protein, which can be used as a 10x stock for subsequent experiments (see section 3).

195 1.1.4.10 To proceed to section 3 of the protocol, work with 100 $\mu\text{l/ml}$ of bead stock, or at a final

196 concentration of 500 nM protein. Note: A good starting point for this procedure will be $2 \cdot 10^{12}$
197 beads/ml, resulting in an average coupling density of $3 \cdot 10^{-4}$ proteins/nm² or an average spacing
198 of 57 nm on a bead of 2 μm diameter.

199 **1.2. Thiol-carboxy directional coupling**

200

201 Note: This protocol is suitable for coupling cysteine containing proteins to carboxyl-
202 functionalized polystyrene beads. The carboxyl moiety is first activated using 1-Ethyl-3-(3-
203 dimethylaminopropyl)carbodiimide (EDC)/ N-hydroxysuccinimide (NHS), amine modified and
204 then cross-linked using Sulfo-SMPB (Figure 2).

205

206 **[Place Figure 2 here]**

207

208 **1.2.1 Preparation of reagents:**

209

210 1.2.1.1 Prepare PBS (100 mM sodium phosphate, 150 mM NaCl, pH 7.0) and autoclave.

211

212 1.2.1.2 Prepare a 100x stock (0.5 M or 287 mg/ml in PBS,) of TCEP immediately before use.

213

214 1.2.1.3 Prepare a 10x stock (20 mM, or 4 mg/ml in PBS) of EDC (1-Ethyl-3-(3-
215 dimethylaminopropyl)carbodiimide) immediately before use.

216

217 1.2.1.4 Prepare a 10x stock (50 mM, or 6 mg/ml in PBS) of NHS (N-hydroxysuccinimide)
218 immediately prior to use.

219

220 1.2.1.5 Prepare a 5x stock (10 mM or 4.58 mg/ml in dH₂O) of Sulfo-SMPB immediately prior to
221 use.

222

223 1.2.1.6 Prepare a 10x stock (500 mM or 88 mg/ml in PBS, pH 7.0) of cysteine immediately
224 before use.

225

226 **1.2.2 Bead activation:**

227

228 1.2.2.1 Mix bead suspension by gently inverting and transfer the required amount of bead
229 suspension (e.g., 12 μl) into a sterile 1.5 ml tube containing 1 ml sterile PBS, pH 7.0.

230 1.2.2.2 Gently pipette up and down to wash the beads and pellet by centrifugation in a
231 microcentrifuge (2 minutes at 16000 x g).

232 1.2.2.3 Carefully remove the supernatant with a pipette and discard.

233 1.2.2.4 Resuspend the bead pellet in 1 ml of fresh sterile PBS and repeat the washing step.

234 1.2.2.5 Resuspend the bead pellet in 0.8 ml of PBS.

235 1.2.2.6 Add 100 µl of 10x EDC stock (2 mM final concentration) and immediately 100 µl of 10x
236 NHS stock solution (5 mM final concentration) to the bead suspension.

237 1.2.2.7 Incubate the bead suspension for 30 minutes at 25 °C on a rotating wheel.

238 1.2.2.8 Wash beads once in 1 ml of PBS and resuspend in 0.8 ml fresh sterile PBS.

239 1.2.2.9 Add 200 µl ethylenediamine, and incubate the bead suspension for 1 hour at 25 °C on a
240 rotating wheel.

241 1.2.2.10 Wash beads once with 1 ml PBS and resuspend the beads in 0.8 ml of fresh PBS.

242 1.2.2.11 Proceed from section 1.1.2.6 (bead activation with Sulfo-SMPB) as described
243 under section 1.1.2 and follow the rest of the protocol described in section 1.1 (Thiol-amine
244 directional coupling). Perform protein preparation and protein coupling steps in a manner
245 identical to those described in section 1.1.

246 Note: The typical coupling efficiency using this protocol is slightly lower (approx. 75%)
247 compared to section 1.1, therefore adjust the initial protein concentration accordingly to
248 achieve the same coupling density.

249 **2. Determination of coupling efficiency**

250 Note: To determine protein concentration, use Bradford Reagent¹⁰ and colorimetric assays as
251 follows:

252 2.1 Gently invert Bradford Reagent to ensure homogeneity of the reagent.

253 2.2 Using a 10 mg/ml BSA stock solution, prepare protein standards covering concentrations
254 from 0.1 to 1.5 mg/ml BSA in buffer.

255 2.3 Add 250 µl of Bradford Reagent to wells of a 96-well plate. Prepare enough wells for all
256 samples, protein standards and negative controls (buffer only).

257 2.4 Add 5 µl of protein sample (protein standards or buffer, for the negative control) to the
258 reagent in the 96-well plate.

259 2.5 Incubate the plate on an orbital shaker at room temperature for 10 minutes.

260 2.6 Measure absorbance at 595 nm using a plate reader.

261 2.7 Generate a standard curve of BSA concentration versus A_{595nm} and use this to
262 determine protein concentrations in initial and supernatant samples.

263 2.8 Calculate the concentration of coupled protein as follows:
264

$$[Coupled\ protein] = [Initial\ protein] - [Supernatant\ protein]$$

265

266 2.9 Calculate the coupling efficiency as:

267

$$Coupling\ efficiency\ (\%) = \frac{[Initial\ protein] - [Supernatant\ protein]}{[Initial\ protein]} \times 100$$

269

270

271 **3. Use of bead-coupled adhesins in competition assays**

272 **3.1 Preparation:**

273 3.1.1 Seed 1 ml per well of Hela cells at a concentration of 150000 cells/ml into a 24-well
274 plate the day before the competition assay, to allow cells to reach approximately 80%
275 confluency prior to starting the experiment.

276 3.1.2 Set up each experimental condition in triplicate. Include wells for negative controls (no
277 bacteria added during competition assays), positive controls (control beads coupled to fusion-
278 tag only added during competition assays) and lysis controls (for cytotoxicity experiments).

279 3.1.3 Inoculate a 5 ml marine LB (MLB) culture with a fresh colony of *V. parahaemolyticus* and
280 grow overnight at 30 °C, shaking.

281 3.1.4 Prepare sufficient bead-coupled MAM, as described in section 1. (Coupling). Allow for
282 100 µl of 10x bead stock per well.

283 **3.2 Competition assay:**

284 3.2.1 On the day of the competition experiment, measure the OD₆₀₀ of the bacterial culture.

285 3.2.2 Prepare infection media by diluting bacterial cultures into colorless DMEM without
286 additives, pre-warmed to 37 °C, containing 10% v/v bead suspension (either adhesin-coupled
287 beads or control beads), to give an MOI of 10. Prepare 1 ml/well and 10-20% excess volume per
288 sample.

289 Note: For the above mentioned conditions (24-well plate, *V. parahaemolyticus*, MOI 10), the
290 necessary volume of overnight culture to be added per well (µl/ml) is calculated as 3/OD₆₀₀ of
291 the culture. For example, 1 ml of infection medium will typically contain 100 µl bead
292 suspension, a few µl of bacterial culture and be made up to 1 ml with colorless,
293 unsupplemented DMEM.

294 3.2.3 Remove old medium from wells and wash cultured Hela cells by adding 1 ml of sterile
295 PBS pre-warmed to 37 °C to each well.

296 3.2.4 Remove PBS and add 1 ml of infection medium per well. Also set up controls, by adding
297 solutions containing control beads and bacteria (positive control) or adhesin beads and no

298 bacteria (negative controls), or DMEM containing 0.1% Triton X-100 (lysis control, only
299 necessary for cytotoxicity measurements).

300 3.2.5 Incubate the plate in a tissue culture incubator at 37 °C for the desired amount of time
301 (e.g. 4 hours for cytotoxicity measurements or 1 hour for adhesion measurements).

302 Note: Both bacterial adhesion and cytotoxicity on host cells can be used as read-outs for the
303 efficacy of inhibition. If the time points of cytotoxicity and adhesion measurements coincide,
304 both assays may be performed using samples from the same well, since cytotoxicity is
305 determined using the culture supernatant and attachment assays use samples derived from the
306 remaining cell layer.

307 **3.3 Cytotoxicity measurements:**

308 3.3.1 At indicated time points (e.g., 4 hours post infection), remove three times 200 µl from
309 each 24-well and transfer to a 96-well plate.

310 3.3.2 Spin 96-well plates at 1500 x g, 5minutes and transfer 100 µl from each well into a fresh
311 96-well plate.

312

313 3.3.3 Add 100 µl of the media used during infection experiments to fresh wells of the 96-well
314 plate in triplicate (these will be used as blanks).

315

316 3.3.4 Carry out the lactate dehydrogenase (LDH) release assay using a LDH cytotoxicity
317 detection kit and following the manufacturer's instructions.

318

319 3.3.4.1 Briefly, calculate the amount of reagent needed in increments of 25 (e.g., if 62 samples
320 are to be measured, make up enough reagent mix for 75 etc.).

321

322 3.3.4.2 For example, for 100 samples, mix 11.25 ml of reagent A with 250 µl of reagent B.
323 Invert, do not vortex to avoid foaming.

324

325 3.3.4.3 Put the mixture in a reservoir to be able to pipet with a multi-channel pipette.

326

327 3.3.4.4 Add 100 µl of reagent mix to each sample.

328

329 3.3.4.5 Incubate plate at room temperature and read the absorbance at 490 nm on a plate
330 reader at 10, 20, 30 minutes.

331

332 3.3.4.6 Analyze the data set for which the absorbance of the lysis control sample is high but still
333 within the linear range of the plate reader (typically, 2-3 absorbance units).

334

335 3.3.4.7 Express results as % cytotoxicity, using the following formula for conversion:

336

$$\text{Cytotoxicity (\%)} = \frac{A490 (\text{sample}) - A490 (\text{blank})}{A490 (\text{triton control}) - A490 (\text{blank})} \cdot 100$$

337

338 **3.4 Measurement of bacterial adhesion:**

339 3.4.1 At indicated time points (e.g., 1 hour post infection), remove media from the cell layer.

340 3.4.2 Thoroughly wash the cell layer with sterile, pre-warmed PBS (at least 3-4 washes of 1 ml
341 PBS each) to remove any un-attached cells.

342 3.4.3 Lyse host cells by adding 1 ml of a sterile 1 % v/v Triton X-100 solution in PBS per well.

343 3.4.4 Incubate the plate at 37 °C for 5 minutes.

344 3.4.5 Pipette each sample up and down several times before transferring the contents of each
345 well to separate 1.5 ml tubes.

346 3.4.6 Prepare 10-fold serial dilutions of samples into sterile PBS (e.g., use 100 µl of sample
347 and 900 µl of PBS).

348 3.4.7 Plate 100 µl of each sample on MLB agar and spread using a cell spreader. Optimize
349 which dilutions to plate depending on the bacterial strains and time point. Note: For the
350 described experimental setup, 10⁵ or 10⁶ fold dilutions give a suitable number of CFUs.

351 3.4.8 Incubate plates at 37 °C overnight and enumerate bacteria by colony counting.

352 **REPRESENTATIVE RESULTS:**

353

354 The *V. parahaemolyticus* adhesin MAM7 contains seven tandem mammalian cell entry (MCE)
355 domains involved in recognition of host surface receptors. We used polystyrene beads coupled
356 to recombinant, purified fragments encompassing either all seven tandem MCE domains
357 (MAM7) or only the first MCE domain (MAM1) to test the ability of these materials to compete
358 with *V. parahaemolyticus* for host cell binding and the resulting efficacy of these materials as
359 adhesion inhibitors. Hela cells were infected with *V. parahaemolyticus* strain POR1, and
360 cytotoxicity resulting from *in vitro* infection was evaluated after 4 hours (Figure 3). Treatment
361 of Hela cells with 0.1% Triton X-100 (positive lysis control) resulted in complete cell lysis,
362 uninfected cells displayed very low levels of cytotoxicity. *In vitro* infection of untreated cells
363 with POR1 resulted in very high levels of cell lysis, and this was inhibited by MAM7-coupled
364 beads but not MAM1-coupled or GST-coupled control beads (Figure 3).

365

366 **[Place Figure 3 here]**

367

368 Enumeration of *V. parahaemolyticus* attached to either untreated Hela cells, or cells incubated
369 with MAM7-, MAM1-, or GST control beads, revealed that MAM7-beads but not MAM1- or
370 GST- control beads outcompete *V. parahaemolyticus* for attachment to host cell surface

371 receptors (Figure 4).

372

373 **[Place Figure 4 here]**

374

375 Adhesins coupled to fluorophore labeled beads result in the generation of materials that mimic
376 bacterial adhesion to host cells and are powerful tools for cellular imaging (Figure 5). Using
377 MAM7-coupled fluorescent blue beads, we characterized the process of MAM7-mediated
378 attachment to epithelial cells. Attachment of MAM7 to host cells resulted in actin
379 rearrangements and formation of stress fibers, which were co-visualized using rhodamine-
380 phalloidin to stain for F-actin (Figure 5B).


381

382 **[Place Figure 5 here]**

383

384 **Figures & Legends:**


385



386


387 **Figure 1: Cross-linking strategy used for directional thiol-amine coupling of proteins to**
388 **polymer beads.** Amine-modified polystyrene beads are activated with Sulfo-SMPB. The
389 maleimide reacts with free cysteines to directionally couple proteins to beads.

390




391

392 **Figure 2: Cross-linking strategy used for directional thiol-carboxyl coupling of proteins to**
393 **polymer beads.** Carboxylated polystyrene beads are first activated with EDC and modified with
394 NHS to form a semi-stable NHS-ester. Subsequent amine-coupling of ethylenediamine results in
395 a free amine group, which reacts with Sulfo-SMPB. Maleimide activated beads can then react
396 with free cysteines to directionally couple proteins to beads.




397
398
399
400
401
402
403
404
405
406
407

Figure 3. Characterization of *Vibrio parahaemolyticus* induced cytotoxicity in epithelial cells during competition assays. Cells were treated with *V. parahaemolyticus* (V.p), indicated with (+), or no bacteria (-) in the presence of different competing entities (comp.) as indicated. These included either no comp. (-), MAM7 beads (MAM7), MAM1 beads (MAM1) or GST control beads (GST). As controls, cells were treated either with Triton X-100 (triton, lysis control), or left uninfected (uninf). LDH release after 4 hours was measured as described in section 3, and results normalized to Triton controls (100 %) and blanks (0 %) as described above. Results are means \pm s.e.m from triplicate experiments.



408
409
410
411
412
413
414
415
416

Figure 4. Characterization of bacterial attachment during competition experiments. HeLa cells were infected with *V. parahaemolyticus* POR2 (V.p. +), in the absence (-) or presence of competing entities (comp.) as follows: MAM7 beads (MAM7), MAM1 beads (MAM1) or GST control beads (GST). Bacterial adhesion was measured after 1 hour, as described in section 3. Results are means \pm s.e.m from triplicate experiments. Means (f.l.t.r. in CFU/ml) are $2.30 \cdot 10^6$, $1.53 \cdot 10^5$, $2.05 \cdot 10^6$, $2.12 \cdot 10^6$.



417
418
419
420

Figure 5. Preparation and use of fluorophore labeled biomimetic beads for imaging purposes. (A) Suspension of fluorescent blue biomimetic beads (right tube, 10x stock) and buffer control

421 (left tube). **(B)** Attachment of MAM7-coupled beads to HeLa cells results in actin
422 rearrangements and stress fiber formation. Attachment of fluorescent blue beads and resulting
423 actin stress fibers (red, stained with rhodamine-phalloidin) were imaged by microscopy. Bar, 10
424 μm . Images in panel B were adapted from Lim *et al.*¹ and reproduced under the Creative
425 Commons Attribution license.

426

427 **DISCUSSION:**

428

429 Herein, we describe two protocols, which can be used to couple thiol-containing proteins to
430 amine- or carboxylate-modified polystyrene beads, respectively. Due to ease of the procedure,
431 thiol-amine coupling is preferable, but depending on the desired bead specification (diameter,
432 fluorescence properties), use of amine-functionalized beads may not be possible and we have
433 therefore included a protocol which will convert the carboxylate- into an amine moiety to give
434 the researcher the greatest possible flexibility in choice of scaffold. Although both thiol-amine
435 and thiol-carboxyl coupling work for any cysteine containing protein, directional coupling (i.e.,
436 immobilization of the protein per its N-terminus, mimicking surface display) requires a protein
437 without cysteine residues, that is produced as a GST fusion protein, or that contains a single
438 terminal cysteine residue introduced by site directed mutagenesis. If multiple reactive cysteines
439 are contained within the protein, this will lead to random immobilization which may impede
440 protein function. Many bacterial adhesins do not contain cysteines naturally. For others, these
441 may be removed by site directed mutagenesis, although this would require extensive assays to
442 ensure native structure and function are retained in the mutant. For GST fusion proteins,
443 purified GST-tag coupled to beads can be used as a suitable negative control. Using uncoupled
444 beads as a control should be avoided, as these often have a higher tendency to clump together
445 or adhere to cells non-specifically. A simplified version of protocol 1.2., using only EDC, can be
446 used to couple proteins to carboxyl-functionalized polymer beads, however in this case
447 coupling takes place via primary amines in the protein and therefore does not guarantee
448 directional coupling.

449

450 TCEP as a reducing agent must not be replaced with other commercially available and
451 commonly used reducing agents, such as dithiothreitol (DTT) or 2-mercaptoethanol (BME), as
452 the thiols contained within them will compete with protein coupling in the thiol-maleimide
453 coupling step. PBS may be replaced with other buffers, but with the following considerations:
454 Buffers may not contain primary amines (so Tris-containing buffers are not suitable). Use of
455 buffers containing very low (< 10mM) salt concentrations leads to bead clumping and should
456 also be avoided. Protein purity is also an important factor to consider during this procedure,
457 and to achieve high quality data, pure proteins should be used. We routinely purify proteins in
458 multiple steps, including at least an affinity purification and gel filtration step, but in some cases
459 ion exchange chromatography is done as a third step. As a result the purity of proteins used for
460 coupling is usually 90% or higher, as judged by SDS-PAGE.

461

462 It is recommended to determine protein concentrations both in the initial reaction mixture as
463 well as of the supernatant after reaction completion. This will help to determine the apparent
464 concentration of bead-coupled protein, and thus coupling density. Determination of both

465 values will also allow calculation of the coupling efficiency. This can be taken into account when
466 preparing the initial protein solution in subsequent reactions, to achieve the desired final
467 concentration and coupling density. Bradford reagent is particularly suited for determination of
468 protein concentration before and after the coupling reaction, as none of the substances in the
469 reaction interferes with the dye complex formation at the concentrations used. If lower protein
470 concentrations are to be used, this method may have to be replaced by a more sensitive
471 detection method, however attention has to be paid to the fact it has to be compatible with the
472 substances contained within the coupling reaction. It is also recommended to use freshly
473 prepared reagents and handle powdered reagents with care (eg, store in a sealed container and
474 use silica beads, to avoid the reagents drawing moisture) since the quality of reagents will
475 influence the coupling efficiency. If the coupling efficiency is lower than expected, possible
476 remedies include increasing the initial bead and protein concentrations. If higher
477 concentrations are being used, the concentration of coupling reagents has to be increased
478 proportionally to ensure sufficient molar excess. Modifying bead/protein concentrations is
479 usually a better step towards optimization rather than increasing reaction times. Since the
480 protocols for bead coupling are lengthy, we commonly prepare a large batch of material.
481 Aliquots of the suspension can be snap-frozen in liquid nitrogen and stored at -20 °C for several
482 months. Thawed aliquots should not be refrozen and should be kept at 4 °C and used within 1-2
483 days. However, this will vary with the nature and stability of the protein used as should be
484 tested on a small batch initially.

485
486 Bead-coupled adhesins can be used for many applications, as discussed below. This protocol
487 described an assay that is commonly used to measure inhibition of bacterial binding and
488 pathogen-mediated cytotoxicity on host cells. The assay is commonly performed to measure
489 the capacity of bead-coupled MAMs to competitively inhibit infection of Hela epithelial cells
490 with the sea-food borne pathogen *Vibrio parahaemolyticus*, using either a decrease in bacterial
491 attachment to host cells or reduced cytotoxicity as a read-out. In both cases, preparation and
492 competition assays follow the same protocol. Depending on the readout, different strains of *V.*
493 *parahaemolyticus* are being used: the cytotoxic strain POR1 is used for cytotoxicity
494 measurements, while the non-cytotoxic strain POR2 is used for measuring bacterial adhesion,
495 since cell death and cell detachment compromises the procedure for quantifying attached
496 bacteria.

497 Initially, competition experiments were set up as a step-wise protocol, where host cells were
498 first pre-incubated with beads prior to the addition of bacteria. For *V. parahaemolyticus* and
499 the bead specifications used (2 µm beads coupled to MAM7), both beads and bacteria can be
500 added at the same time without changes in the resulting cytotoxicity. I.e., in this experimental
501 setup, beads outcompete bacteria for host cell binding. Depending on the bacterial species and
502 bead geometry used, there may be good reasons for maintaining the bead adhesion and
503 bacterial infection as two separate steps. For example, to infect cells with non-motile bacteria,
504 plates are commonly centrifuged after addition of the infection media. However, centrifugation
505 of plates containing bead suspensions should be avoided, since this leads to a highly uneven
506 distribution of beads on the cell layer. If smaller particle sizes are being used, beads will take
507 longer to settle on the cell surface, in which case sufficient time should be allowed for bead

508 attachment prior to the infection. When bacterial adhesion is used as a read out, samples
509 should be taken at time points where host cells are not significantly damaged by the infecting
510 strain, as cell detachment and lysis can compromise the quantification of attached bacteria.

511
512 Instead of enumerating bacterial adhesion by dilution plating, samples may alternatively
513 be processed for imaging (Figure 5). In this case, tissue culture cells should be seeded onto glass
514 cover slips, rather than directly into wells. Additionally, fluorescent beads and bacteria
515 expressing a fluorescent protein may be used, along with infection-specific host cell markers.
516 For example, competition experiments are commonly imaged using fluorescent red rhodamine-
517 phalloidin to stain the host cells' actin cytoskeleton and assess morphological changes resulting
518 from infection, together with fluorescent blue beads and fluorescent green (GFP expressing or
519 SYTO18 stained) bacteria.

520
521 A range of bead-coupled adhesins, including *Staphylococcus aureus* FnBPA, *Streptococcus*
522 *pyogenes* F1 FUD and *Vibrio parahaemolyticus* MAM, have been used as biomimetic materials
523 to study adhesion, adhesion inhibition and the contribution of adhesion to pathogen-mediated
524 cytotoxicity^{1, 7, 8}. One of the advantages of using this approach is the ease of visualization of
525 attachment events, since the polymer beads used as scaffolds are available in a wide range of
526 colors (e.g., blue, fluorescent red, blue, green, orange). Thus, direct protein labeling, which may
527 interfere with function, can be avoided. Additionally, surface coupling mimics the multivalent
528 display of adhesins on the bacterial surface, thus reflecting a more physiologically relevant
529 conformation compared to soluble proteins.

530
531 Compared to studies using intact bacteria or bacterial mutants, the bead approach circumvents
532 problems associated with bacterial growth. For example, longer-term (e.g., overnight) studies
533 of bacterial adhesion to host cells using intact bacteria are often compromised by phenomena
534 accompanying bacterial growth – acidification of the growth medium and nutrient depletion
535 negatively affect host cells, and bacterial replication eventually compromises imaging quality.

536
537 More recently, the use of bead-coupled adhesins has been extended to include their use as
538 tools for affinity purifications of host cellular factors involved in signaling processes
539 downstream of bacterial attachment. *V. parahaemolyticus* MAM7, via binding to phosphatidic
540 acids in the host cell membrane, triggers RhoA activation and actin rearrangements^{1, 3}. MAM-
541 coupled beads are being used to purify and identify proteins involved in the signaling platforms
542 assembled as a consequence of MAM-host cell binding. Since beads can easily be separated
543 from the supernatant by a short centrifugation step, and the protein of interest is covalently
544 coupled, this is a good method to achieve separation from contaminant proteins and enrich
545 relevant protein complexes, which can be used for downstream applications such as
546 proteomics or Western Blotting.

547
548 **ACKNOWLEDGMENTS:**

549
550 The authors would like to thank members of the Krachler group for critical reading of the
551 manuscript. DHS, DV and AMK were funded by the Biotechnology and Biological Sciences

552 Research Council (BB/L007916/1), FA was funded by a Republic of Iraq Ministry of Higher
553 Education and Scientific Research Scholarship and NPS was funded by a CONICYT Scholarship.

554

555 **DISCLOSURES:**

556

557 The authors have nothing to disclose.

558

559 **REFERENCES**

560

561 1. Lim, J., Stones, D. H., Hawley, C. A., Watson, C. A. & Krachler, A. M. Multivalent Adhesion
562 Molecule 7 clusters act as signaling platform for host cellular GTPase activation and facilitate
563 epithelial barrier dysfunction. *PLoS Pathog* **10** (9), e1004421, doi:10.1371/journal.ppat.1004421
564 (2014).

565 2. Krachler, A. M., Ham, H. & Orth, K. Outer membrane adhesion factor multivalent
566 adhesion molecule 7 initiates host cell binding during infection by gram-negative pathogens.
567 *Proc Natl Acad Sci U S A* **108** (28), 11614-11619, doi:10.1073/pnas.1102360108 (2011).

568 3. Krachler, A. M. & Orth, K. Functional characterization of the interaction between
569 bacterial adhesin multivalent adhesion molecule 7 (MAM7) protein and its host cell ligands. *J*
570 *Biol Chem* **286** (45), 38939-38947, doi:10.1074/jbc.M111.291377 (2011).

571 4. Joh, D., Speziale, P., Gurusiddappa, S., Manor, J. & Hook, M. Multiple specificities of the
572 staphylococcal and streptococcal fibronectin-binding microbial surface components recognizing
573 adhesive matrix molecules. *Eur J Biochem* **258** (2), 897-905, doi:10.1046/j.1432-
574 1327.1998.2580897.x (1998).

575 5. Bingham, R. J. *et al.* Crystal structures of fibronectin-binding sites from *Staphylococcus*
576 *aureus* FnBPA in complex with fibronectin domains. *Proc Natl Acad Sci U S A* **105** (34), 12254-
577 12258, doi:10.1073/pnas.0803556105 (2008).

578 6. Ensenberger, M. G. *et al.* Specific interactions between F1 adhesin of *Streptococcus*
579 *pyogenes* and N-terminal modules of fibronectin. *J Biol Chem* **276** (38), 35606-35613,
580 doi:10.1074/jbc.M105417200 (2001).

581 7. Hawley, C. A., Watson, C. A., Orth, K. & Krachler, A. M. A MAM7 peptide-based inhibitor
582 of *Staphylococcus aureus* adhesion does not interfere with in vitro host cell function. *PLoS One*
583 **8** (11), e81216, doi:10.1371/journal.pone.0081216 (2013).

584 8. Krachler, A. M., Ham, H. & Orth, K. Turnabout is fair play: use of the bacterial
585 Multivalent Adhesion Molecule 7 as an antimicrobial agent. *Virulence* **3** (1), 68-71,
586 doi:10.4161/viru.3.1.18172 (2012).

587 9. Krachler, A. M., Mende, K., Murray, C. & Orth, K. In vitro characterization of multivalent
588 adhesion molecule 7-based inhibition of multidrug-resistant bacteria isolated from wounded
589 military personnel. *Virulence* **3** (4), 389-399, doi:10.4161/viru.20816 (2012).

590 10. Bradford, M. M. A rapid and sensitive method for the quantitation of microgram
591 quantities of protein utilizing the principle of protein-dye binding. *Anal Biochem* **72**, 248-254,
592 doi:10.1016/0003-2697(76)90527-3 (1976).

593

594